

**ESKA™ OPTOHOME Poly-Vinyl-Chloride Jacketed Optical Fiber Cord: RHVV4002-CMR**

**Manufactured by Mitsubishi Rayon Co., Ltd.**

Marketed and sold by Mitsubishi International Corporation

March 2011

Structure		
Core Material	Polymethyl Methacrylate Resin (PMMA)	
Cladding Material	Fluorinated Polymer	
Core Refractive Index	1.49	
Refractive Index Profile	Step Index	
Numerical Aperture	0.5	
	Unit	Typical
Core Diameter	μm	980
Cladding Diameter	μm	1,000
Number of Fibers	2	
Jacket Color and Material	Black, Poly-Vinyl-Chloride	
Outer Sheath Dimension - Minor Axis	mm	2.2
Outer Sheath Dimension - Major Axis	mm	4.4
Approximate Weight	g/m	11

Packaging	
Spool Length (m)	500
Net weight on spool (kg)	6.6
Spool Weight (kg)	1.2
Carton Size (mm)	365 X 365 X 160
Carton Weight (kg)	7.2
Master Carton	5 spools
Outer Sheath	
Color and Material	White, Poly-Vinyl-Chloride
Indication on Outer Sheath	Green; (UL)E336876 MITSUBISHI RAYON ESKA OPTOHOME TYPE OFNR FT4
Fire Rating	Riser OFNR FT4

Performance		Criteria for Acceptance and/or [Test Conditions]	Unit	Values
Operation Temperature		No deterioration in optical properties [in a dry atmosphere]*	°C	-55 ~ 70
Operating Temperature in a Moist Atmosphere		No deterioration in optical properties [under 95% RH] **	°C	Max.60
Optical Properties	Transmission Loss [650nm Collimated Light]	[25°C 50% RH]	dB/km	Max.170
		[Operation Temperature]	dB/km	Max.190
	Bandwidth	[launch NA > Fiber NA]	MHz · 50m	Min.40
Mechanical Characteristics	Minimum Bend Radius	Loss increment =< 0.5dB [a quarter bend]***	mm	Min.25
	Repeated Bending Endurance	Loss increment =< 1 dB [in conformity to the JIS C 6861]****	Times	Min.5,000
	Tensile Strength	[Tensile force at 5% Elongation; in conformity to the JIS C 6861]	N	Min.140
	Twisting Endurance	Loss Increment =< 1 dB [sample length: 1m, Tensile Force: 4.9N]	Times	-
	Impact Endurance	Loss Increment =< 1 dB [in Conformity to the JIS C 6861]	N · m	-

Notes: Performance tested in conditions under 25°C unless otherwise indicated.

\* Attenuation increase shall be <10% after 1,000 hours.

\*\* Attenuation increase shall be <10% after 1,000 hours, except when due to absorbed water.

\*\*\* In the direction of the minor axis.

\*\*\*\* Bend Angle +/-90°C, Bend Radius 15mm, Tension 1,000g.

**Applications**

RHVV4002-CMR is for home networking applications with fire retardancy requirement..

The information contained herein is presented as a guide to product selection. It is subject to change without notice, and should not be regarded as a representation, warranty or guarantee with regard to the quality, characteristics or use of this product



655 Third Avenue New York, NY 10017

Please visit <http://www.fiberopticpof.com/> to locate a sales representative near you.