

Specification Sheet

VK-100
(MAP-5749-2)

High-Performance Plastic Optical Fiber

Eska™

MITSUBISHI RAYON CO.,LTD.

ESKA OPTICAL FIBER DIVISION

1-1, Marunouchi 1-Chome, Chiyoda-ku, Tokyo 100-8253, Japan

Phone :+81-3-6748-7518

Facsimile:+81-3-3286-1366


1. Scope
This specification covers basic requirements for the structure and optical performances of VK-100.
2. Structure

Table 1

VK-100

Item		Specification			
		Unit	Min.	Typ.	Max.
Optical Fiber	Core Material	—	Polymethyl-Methacrylate Resin		
	Cladding Material	—	Fluorinated Polymer		
	Core Refractive Index	—	1.49		
	Refractive Index Profile	—	Step Index		
	Numerical Aperture	—	—	0.5	—
	Core Diameter	μm	—	28	—
	Number of cores	—	7095		
	Fiber Diameter	μm	2350	2,500	2,650
Approximate Weight		g/m	6.5		

Sectional View



Optical Fiber

3. Performances

Table 2

		VK-100				
Item		Acceptance Criterion and/or [Test Condition]	Specification			
			Unit	Min.	Typ.	Max.
Maximum Rating	Storage Temperature	No Physical Deterioration [in a Dry Atmosphere]	°C	-40	-	+60
	Operation Temperature	No Deterioration in Optical Properties* [in a Dry Atmosphere]	°C	0	-	+60
		No Deterioration in Optical Properties** [under 95%RH condition]	°C	-	-	+50
Optical Properties***	Transmission Loss [650nm Collimated Light]	[25°C 50%RH]	dB/km	-	-	350
Mechanical Characteristics	Minimum Bend Radius	Loss Increment ≤ 0.5 dB [A Quarter Bend]	mm	1	-	-
	Tensile Strength	Tensile Force at 5% Elongation; in Conformity to the JIS C 6861]	N	350	-	-

All tests are carried out under temperature of 25°C unless otherwise specified.

* Attenuation change shall be within +/- 10% after 1,000 hours.

** Attenuation change shall be within +/- 10% after 1,000 hours, except that due to absorbed water.

*** The number of dead cores or sick cores is less than or equal 10 pixels.

4. Revision

REVISION No.	DATE	REMARK	DRAWN	APPVD
	Dec,04,2012	new issue	Takenaka	Okita
-1	Aug,14,2013	We deleted the DRAFT.	Takenaka	Okita
-2	Sep,09,2013	Correction	Takenaka	Okita