
## 1. Scope

This specification covers basic requirements for the structure and optical performances of GHN-4001-B

## 2. Structure

Table 1				GHN-4001-B			
Item		Specification					
		Unit	Min.	Тур.	Max.		
Optical Fiber	Core Material	_	Polymethyl-Methacrylate Resin				
	Cladding Material	_	Fluorinated Polymer				
	Core Refractive Index	_	1.49				
	Refractive Index Profile	_	Step Index				
	Numerical Aperture	_	0.5				
	Core Diameter	μm	920	980	1,040		
	Cladding Diameter	μm	940	1,000	1,060		
Jacket	Material	_	Polyamide				
	Color	_	Black				
	Diameter	mm	2.13	2.20	2.27		
Approximate Weight		g/m	4				
Indication on the Jacket		_	None				

## **Sectional View**



## 3. Performances

Table 2			GHN-4001-B				
Item		Acceptance Criterion and/or [ Test Condition ]	Specification				
			Unit	Min.	Тур.	Max.	
Maximum Rating	Storage Temperature	No Physical Deterioration [ in a Dry Atmosphere ]	${\mathbb C}$	-55	_	+85	
	Operation Temperature	No Deterioration in Optical Properties [in a Dry Atmosphere]	${\mathbb C}$	-55	_	+85	
		No Deterioration in Optical Properties** [ under 95%RH condition ]	${\mathbb C}$	_	_	+75	
Optical Properties	Transmission Loss [ 650nm Collimated Light ]	[ 25°C 50%RH ]	dB/km	_	_	170	
		[ Operation Temperature ]	dB/km	_	_	190	
Mechanical Characteristics	Minimum Bend Radius	Loss Increment ≦0.5dB [ A Quarter Bend ]	mm	25	_	-	
	Repeated Bending Endurance	Loss Increment ≦1dB [ in Conformity to the JIS C 6861 ]***	Times	5,000	_	I	
	Tensile Strength	Tensile Force at 5% Elongation; in Conformity to the JIS C 6861 ]	N	70	_	ı	
	Twisting Endurance	Loss Increment ≦1dB [ Sample Length : 1m Tensile Force : 4.9N ]	Times	5	_	_	
	Impact Endurance	Loss Increment ≦1dB [ in Conformity to the JIS C 6861 ]	N∙m	0.4	_	_	

All tests are carried out under temperature of 25°C unless otherwise specified.

The specifications is subject to change without notice.

The information contained herein is presented as guide for the product selection.

Please contact our business department for the issue of an official specification sheet.

<sup>\*</sup> Attenuation change shall be within +/- 10% after 1,000 hours.

<sup>\*\*</sup> Attenuation change shall be within +/- 10% after 1,000 hours, except that due to absorbed water.

<sup>\*\*\*</sup> Bend Angle +/-90° ,Bend Radius 15mm,Tension 500g