No


1. Scope

This specification covers basic requirements for the structure and optical performances of SH-1001-1.0.

2. Structure

Table 1				SH-1001-1.0			
Item .		Specification					
		Unit	Min. Typ. Max.				
Optical Fiber	Core Material	_	Polymethyl-Methacrylate Resin				
	Cladding Material	_	Fluorinated Polymer				
	Core Refractive Index	_	1.49				
	Refractive Index Profile	_	Step Index				
	Numerical Aperture	_	0.5				
	Core Diameter	μm	217	240	263		
	Cladding Diameter	μm	227	250	273		
Jacket	Material	_	Polyethylene				
	Color	_	Black				
	Diameter	mm	0.95	1.00	1.05		
Approximate Weight		g/m	0.7				
Indication on the Jacket		_	None				

Sectional View



No

3. Performances

-	_			$\overline{}$
	2	n	Δ	٠,

Table 2				SH-1001-1.0			
ltem		Acceptance Criterion and/or	Specification				
		[Test Condition]	Unit	Min.	Тур.	Max.	
Maximum Rating	Storage Temperature	No Physical Deterioration [in a Dry Atmosphere]	$^{\circ}\!\mathbb{C}$	-55	-	+70	
	Operation Temperature	No Deterioration in Optical Properties [*] [in a Dry Atmosphere]	$^{\circ}\!$	-55	_	+70	
		No Deterioration in Optical Properties** [under 95%RH condition]	$^{\circ}$ C	ı	ı	+60	
Optical Properties	Transmission Loss [650nm Collimated Light]	[25°C 50%RH]	dB/km	1	1	400	
		[Operation Temperature]	dB/km	1	1	420	
Mechanical Characteristics	Minimum Bend Radius	Loss Increment ≦0.5dB [A Quarter Bend]	mm	5	1	1	
	Repeated Bending Endurance	Loss Increment ≦1dB [in Conformity to the JIS C 6861]***	Times	_	-		
	Tensile Strength	Tensile Force at 5% Elongation [in Conformity to the JIS C 6861]	N	4	_	_	
	Twisting Endurance	Loss Increment ≦1dB [Sample Length : 1m Tensile Force : 4.9N]	Times	_	_	_	
	Impact Endurance	Loss Increment ≦1dB [in Conformity to the JIS C 6861]	N∙m	_	_	_	

All tests are carried out under temperature of 25°C unless otherwise specified.

The specifications is subject to change without notice.

The information contained herein is presented as guide for the product selection.

Please contact our business department for the issue of an official specification sheet.

^{*} Attenuation change shall be within +/- 10% after 1,000 hours.

^{**} Attenuation change shall be within +/- 10% after 1,000 hours, except that due to absorbed water.

^{***} Bend Angle +/-90° ,Bend Radius 15mm,Tension 500g